


*Data sheet*

**902.00900**

**PEELABLE CLEARCOAT**



1000 ml +  
100 - 200 ml



Ø 1.8 – 2.2 mm  
4-5 Atm  
N° of coats 2



Drying 20 °C 10'/15'  
Curing 20 °C:4/5 hours



Application by  
brush

**NATURE OF PRODUCT:**

Finishing coat based on vinyl resins and plasticizing additives.

**FIELD OF APPLICATION:**

Very fast-drying tear-off paint, suitable for protection of steelwork, industrial carpentry.

**PREPARATION OF THE SUBSTRATE:**

Remove all traces of grease and moisture by thorough degreasing of the surface to be painted.

**PREPARATION OF THE PRODUCT:**

Peelable: **902.00900** 100 parts by weight  
Diluent: **D.525** 15 – 20 parts by weight

To remove coating, cut the film thickness into squares and peel normally, or use a hot water pressure washer. Thicknesses of no less than 80 microns are recommended for the paint to tear better.

**PRODUCT SPECIFICATIONS:**

**TYPE OF PRODUCT** : Single-component.  
**APPEARANCE OF THE FILM** : Glossy  
**COLORS** : Clear  
**SPECIFIC WEIGHT** : 0,89 Kg/Lt (± 0,05)  
**SUPPLY VISCOSITY** : 25" (± 4) ford 8 at 25 °C  
**DRY RESIDUE** : 29% (± 2)  
**DRYING AT 20 °C** : - *Dry dust-free* : 10' - 15'  
: - *Drying* : 4 - 5 hours at 20 °C.  
**RECOMMENDED LAYERS** : A cross coat  
**RECOMMENDED THICKNES** : 80 - 90 micron  
**THEORETICAL YIELD** : 3 m<sup>2</sup>/Kg-Lt at 80 microns dry

### **SAFETY REGULATIONS:**

Strictly follow the instructions on the labeling and in the safety data sheet.

### **STORAGE CONDITIONS:**

In unopened and sealed packages, kept at a temperature of +5 to +30 °C.

*The data and information contained in this sheet are the result of our experience and accurate laboratory tests. However, since the painting process represents a set of operations that are beyond our control, they do not therefore guarantee, in any way, the final performance of the cycle.*

**Rev.: 04/22**