


Data sheet

922.90900

WHITE PEELABLE



1000 ml +
100 - 200 ml



Ø 1.8 - 2.2 mm
4 - 5 Atm
N° of coats 2



Dry dust-free 20 °C 10'/15'
Curing 20 °C:4/5 hours



Application by
brush

NATURE OF PRODUCT:

Finishing coat based on vinyl resins and plasticizing additives.

FIELD OF APPLICATION:

Very fast-drying tear-off paint, suitable for protection of steelwork, industrial carpentry.

PREPARATION OF THE SUBSTRATE:

Remove all traces of grease and moisture by thorough degreasing of the surface to be painted.

PREPARATION OF THE PRODUCT:

Peelable: **922.90900** 100 parts by weight
Diluent: **D.525** 10 - 20 parts by weight

To remove coating, cut the film thickness into squares and peel normally, or use a hot water pressure washer.

Thicknesses of no less than 80 microns are recommended for the paint to tear better.

PRODUCT SPECIFICATIONS:

TYPE OF PRODUCT : Single-component.
APPEARANCE OF THE FILM : Glossy
COLORS : White
SPECIFIC WEIGHT : 0,94 Kg/Lt (± 0,05)
SUPPLY VISCOSITY : 25" (± 4) ford 8 at 25 °C
DRY RESIDUE : 34% (± 2)
DRYING AT 20 °C : - *Dry dust-free* : 10' - 15'
: - *Drying* : 4 - 5 hours at 20 °C
RECOMMENDED LAYERS : A cross coat
RECOMMENDED THICKNES : 80 - 90 micron
THEORETICAL YIELD : 3.3 m²/Kg-Lt at 80 microns dry

SAFETY REGULATIONS:

Strictly follow the instructions on the labeling and in the safety data sheet.

STORAGE CONDITIONS:

In unopened and sealed packages, kept at a temperature of +5 to +30 °C.

The data and information contained in this sheet are the result of our experience and accurate laboratory tests. However, since the painting process represents a set of operations that are beyond our control, they do not therefore guarantee, in any way, the final performance of the cycle.

Rev.: 04/22