


Data sheet


Series 624

K.624

BRUSH-ON SYNTHETIC MATTE CONVERTER



1000 +
30 - 50



20" - 22" FORD 4
at 20 °C



Drying: 1h - 2h
Curing: 24h - 36h



Application
by brush
N° of coats 2



Application
by roller

NATURE OF PRODUCT:

Brush-on high quality and high strength synthetic matte enamel It can be applied to both wood and iron after careful selection of the appropriate type of primer. The applied film remains elastic and adherent even after prolonged outdoor exposure.

FIELD OF APPLICATION:

Decorative enamel for furniture, fixtures, metalwork, agricultural machinery, etc.

PREPARATION OF THE SUBSTRATE:

Iron surfaces: Thoroughly remove all traces of rust, calamine, grease and moisture. Old paints with poor adhesion should be removed by sanding. Apply 1 or 2 coats of primer. After about 24 hours, apply the enamel finish by brush.

Aluminum surfaces: To achieve maximum adhesion on this substrate, the traditional anti-corrosive product is replaced with specific primer such as our **994.90900** white or **994.90100** black.

Wood surfaces: On new wood, apply one or two coats of polyurethane primer or other suitable primer. After the primer dries, sand thoroughly with sandpaper and then apply one or two coats of finishing enamel.

PREPARATION OF THE PRODUCT:

Comp. A:	K.624 + (Coloring Pastes)	100 parts by weight
Diluent:	D.434	3 - 5 parts by weight

APPLICATION:

By brush, by roller by spray.

PRODUCT SPECIFICATIONS:

TYPE OF PRODUCT	: Single-component.
APPEARANCE OF THE FILM	: Matte.
COLORS	: By choice
DENSITY	: 1,04 Kg/l ($\pm 0,05$)
SUPPLY VISCOSITY	: 30" (± 5) DIN 8 at 20 °C
SOLID CONTENT	: 62% ($\pm 2\%$)
DRYING	: - <i>Dry dust-free</i> : 1h – 2h : - <i>Print-free</i> : 7h – 8h : - <i>Complete Curing</i> : 24h – 36h
RECOMMENDED LAYERS	: 2 coats
RECOMMENDED THICKNESS	: 30 - 40 μm
OPACITY	: 15 Gloss (± 4) depending on the color and thickness applied
THEORETICAL YIELD ⁽¹⁾	: 11,3 m ² /Lt or 9,8 m ² /Kg at 50 μm dry

⁽¹⁾ In ratio 80/20 with **P.900**

RECOATING:

After 24 hours minimum. For product obtained by industrial dyeing, repaint wet-on-wet or within 4 to 6 hours, or 1/2 weeks after the first coat.

SAFETY REGULATIONS:

Strictly follow the instructions on the labeling and in the safety data sheet.

STORAGE CONDITIONS:

The storage room must be dry and with a temperature between +10 °C and +35 °C.

The data and information contained in this sheet are the result of our experience and accurate laboratory tests. However, since the painting process represents a set of operations that are beyond our control, they do not therefore guarantee, in any way, the final performance of the cycle.

Rev.: 05/22